

根据客户要求定制规格：长度，尺寸，公差和粗糙度等。
Customized specifications according to customers' requirements: length, dimensions, tolerances, roughness, etc.

元素符号		成分%	元素符号		成分%
Element symbol		Composition%	Element symbol		Composition%
铬	Cr	32.0-35.0	钨	W	4.3-5.5
铝	Al	0.70-1.30	铁	Fe	≤0.5
钼	Mo	2.3-3.5	硅	Si	≤0.3
钛	Ti	0.70-1.30	镍	Ni	余量/Balance
碳	C	0.03-0.10	铌	Nb	0.7-1.3
铈	Ce	≤0.030	硼	B	≤0.008

试验温度 Test temp (℃)	抗拉强度 Tensile strenght (MPa)	屈服强度 Yield strenght (MPa)	延伸率 Elogation (%)	断面收缩率 Reduction of area (%)	试验温度 Test temp (℃)	试验应力 Test stress (MPa)	持续时间 Duration (h)	延伸率 Elongation (%)
室温 RT	≥780	—	≥4	—	—	—	—	—
—	—	—	—	—	800	206	≥40	—